

SYNTHESO GLK 0, GLK 1

Special lubricating greases for elastomers



Benefits for your application

- **Special lubricants for the assembly and lifetime lubrication of elastomers**
- **Almost neutral towards EPDM/metal or plastic sliding material combinations**

Description

SYNTHESO GLK 0 and GLK 1 are special lubricating greases for a wide variety of applications with an almost neutral behaviour towards many elastomers (also EPDM) and plastics. Both products offer excellent wear protection, high load-carrying capacity, good adhesion and resistance to water.

Application

SYNTHESO GLK 0 and GLK 1 have been designed for the lubrication of elastomer – metal, plastic – metal, plastic – plastic, as well as metal – metal sliding material combinations. The products are typically used in the automotive industry as assembly greases for plain bearings. E.g. in brake and clutch systems for linear motion in contact with brake fluids DOT 3, 4 and 5.1. Application examples: guide bushes, bolts, EPDM and SBR seals, clutch master and slave cylinders, corrosion protection of brake shoe supports in disc brake callipers. In all such applications, SYNTHESO GLK0 and GLK1 facilitate damage

free assembly and provide reliable long term lubrication. SYNTHESO GLK 0 and GLK 1 can also be used for the lubrication of plain bearings with low sliding velocities and for the lubrication of small plastic gears.

Application notes

A wear test should be carried out prior to using SYNTHESO GLK 0 and GLK 1 in context with aluminium or aluminium alloys under dynamically high load conditions. Owing to the many different elastomer and plastic compositions we recommend checking their compatibility prior to series application.

Material safety data sheets

Material safety data sheets can be downloaded or requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	SYNTHESO GLK 0	SYNTHESO GLK 1
Can 1 kg	-	+
Bucket 25 kg	+	+
Drum 180 kg	+	+



SYNTHESO GLK 0, GLK 1

Special lubricating greases for elastomers

Product data	SYNTHESO GLK 0	SYNTHESO GLK 1
Article number	012134	012126
Lower service temperature	-40 °C / -40 °F	-40 °C / -40 °F
Upper service temperature	150 °C / 302 °F	150 °C / 302 °F
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 40 °C	approx. 363 mm ² /s	approx. 363 mm ² /s
Worked penetration, DIN ISO 2137, 25 °C, upper limit value	375 x 0.1 mm	315 x 0.1 mm
Worked penetration, DIN ISO 2137, 25 °C, lower limit value	355 x 0.1 mm	285 x 0.1 mm
Chemical composition, thickener	special lithium soap	special lithium soap
Chemical composition, type of oil	PAG	PAG
Density at 20 °C	approx. 0.97 g/cm ³	approx. 0.97 g/cm ³
Drop point, DIN ISO 2176	>= 220 °C	>= 250 °C
Texture	homogeneous	homogeneous
Texture	fibrous	long-fibred
Colour space	beige	beige
Water resistance, DIN 51807 pt. 01, 3 h/90 °C, rating	<= 1 - 90	<= 1 - 90
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	36 months	36 months

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

**Klüber Lubrication München SE & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.**

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.



a company of the Freudenberg Group